

## TECHNICAL DATA SHEET

# FLOORGUARD 5000

## FLOORGUARD SF GLASS FLAKE REINFORCED EPOXY COATING

**DESCRIPTION:** A two component , solvent free epoxy coating based on inorganic minerals reinforced with specially selected glass flake. Offers good chemical and abrasion resistance.

**RECOMMENDED USE:** The system is designed for steel decks and concrete floors subjected to medium foot and rubber tired vehicle traffic. Also suitable for walls and areas of the intermittent chemical spills and power washing. Ideally suited for use in:

1. Hospitals	2. Dairies	3. Warehouses
4. Chemical plants	5. Car parks	6. Meat & poultry plant

### APPROVALS AND CERTIFICATES

Determination of shore 'A' hardness – ASTM D 2240  
Determination of compressive strength – ASTM C579  
Determination of taber abrasion CS 17, 1000 g -ASTM D4060  
Additional certificates and approvals may be available on request.

### PRODUCT INFORMATION:

Colour availability	Grey & Limited colors
Finish:	Semi-gloss & High-Gloss
Volume solids %:	100 % (ASTM-D2697-86)
V.O.C.:	0 g/l (NB. Thinning will affect VOC compliance and volume solids)
Flash point:	Base : > 100°C C/A : > 100°C
Mixing ratio:	2 parts base to 1 part curing agent by volume
Shelf life:	24 months from the date of manufacture.
Pot life:	20 minutes @ 35°C
Pack size:	15 Litres unit when mixed.

FILM THICKNESS AND SPREADING RATE:	MIN.	MAX.
Dry film thickness	200μ	1mm
Wet film thickness	200μ	1mm
Spreading rate(m <sup>2</sup> / Litre)	5	1

This figure makes no allowance for surface profile, uneven application, overspray or losses in containers and equipment. Film thickness will vary depending on actual use and specification. Please contact KPC technical team for applying higher DFT.)

**SERVICE TEMPERATURE:** 120°C Maximum Dry.

**RECOMMENDED THINNER:** Thinner is not required

مجموعة الباطين  
ALBATAIN GROUP



صباحان الصناعية - قطعة 8 - قسيمة 162 - شارع 81  
ص.ب: 42255 - الشويخ الصناعية - الكويت  
هاتف: 24832644 - 24832698 - 24832557 - فاكس: 24843971

Sabhan Industrial - Block 8 - Avenue 162 - Street 81  
P.O. Box 42255 - Shuwaikh Industrial, 70653 Kuwait  
Tel. : +965 24832644 - 24832698 - 24832557 - Fax : +965 24843971

# FLOORGUARD 5000

## FLOORGUARD SF GLASS FLAKE REINFORCED EPOXY COATING

### FILM THICKNESS AND SPREADING RATE: MIN. MAX. UNIT

Dry film thickness	100	200	μm
Wet film thickness	154	308	μm
Spreading rate	6.45	3.25	m <sup>2</sup> /l (theoretical)

This figure makes no allowance for surface profile, uneven application, overspray or losses in containers and equipment. Film thickness will vary depending on actual use and specification.

### SURFACE PREPARATION:

**New Construction:** Concrete floors, to be coated should be allowed to cure for atleast 28 days. Floor should be sound, clean and free from oils, grease, mortar, loose particles, dust etc. Laitance should be removed by the use of mechanical means such as vacuum recovery shot blasting. Moisture content should be less than 5%.

**Existing substrate:** All contamination must be removed and a sound clean substrate should be exposed. Mechanical means of preparation are preferred followed by the removal of dust and other loose debris using an industrial vacuum. All cracks and minor damage-surface should be repaired and allow to dry prior to priming.

### RECOMMENDED COATING SYSTEM:

PRIMER	FLOORGUARD 230 (concrete), PERMAGUARD P270 (steel)
PUTTY	PERMAFILL F 202 / PERMAFILL F 303
TOPCOAT	FLOORGUARD 5000

### RECOMMENDED APPLICATION METHODS:

Airless Spray, trowel, roller or brush (touch-up)

### APPLICATION EQUIPMENT DETAILS:

AIRLESS SPRAY:	Nozzle Size: 0.44mm (18 thou)
	Fan Angle: 40°
	Operating Pressure: 115kg/cm <sup>2</sup> (2200 psi)

# FLOORGUARD 5000

## FLOORGUARD SF GLASS FLAKE REINFORCED EPOXY COATING

### MIXING INSTRUCTIONS:

Materials are supplied in two containers, Base and Curing Agent. Stir thoroughly both the materials separately using a power agitator. Then add complete contents of Curing agent to Base whilst using the power agitator to mix properly. Use the mixed material within the specified working pot life.

### APPLICATION CONDITIONS AND OVER COATINGS:

New concrete should be allowed to cure for a minimum of 30 days and have a moisture content of less than 5%. Very dense, non porous or chemically treated concrete may require acid etching, abrasive blasting or sanding for optimum adhesion. This material should preferably be applied at temperatures in excess of 10°C. In conditions of high relative humidity, i.e. 80-85%, good ventilation conditions are essential. Substrate temperature should be at least 3°C above the dew point and always above 0°C. At application temperatures below 10°C, drying and curing times will be significantly extended, and spraying characteristics may be impaired. Application at ambient air temperatures below 5°C is not recommended.

### NON-SLIP FINISH:

If a non-slip surface is required then apply primer coat first. While the coat is still wet broadcast KPC's Non-slip Aggregate to the required density. Allow curing to initial hardness, 4-6 hours, and vacuum clean the excess aggregate. Apply the topcoat using a medium haired roller and ensure that a continuous film is achieved while ensuring that the aggregate is completely sealed.

### HEALTH AND SAFETY:

Please observe the precautionary notices displayed on the container. Do not breathe or inhale mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Consult Product Health and Material Safety Data Sheet for information on safe storage, handling and application of this product.

**Disclaimer:** The information in this document is given to the best of KPC Paint's knowledge that based on laboratory testing and practical experience Products are often used under conditions beyond KPC's control and KPC Paints cannot guarantee anything but the quality of the product itself.